



## Di Octyl Phthalate

Test Description	Test Method	Unit of Measure	Specification
Density @20°C	JIS K6751	g/ml	0.986 ± 0.003
Refractive Index	JIS K6751	°C	1.485 ± 0.003
Color	JIS K6751	APHA	max 18
Acid Value	JIS K6751	KOH mg/g	max 0.02
Heat Loss (125°C, 3hr)	JIS K6751	% wt.	max 0.06
Ester Content	GC	% wt.	min 99.60
Volume Resistivity (30 °C)	JIS K6751	Ω-cm	min 4 x 10 <sup>11</sup>
Water Content	Karl Fischer	% wt.	-
Acid Value after heating	JIS K6751	KOH mg/g	-

Comments: Physical properties are not monitored constantly.

Issue of revision date: 21.10.2020

—  
Spec Version:1